ersion 1

 $CaSO_4$ 

**Crystal Data:** Orthorhombic. Point Group: 2/m 2/m 2/m. Crystals tabular on  $\{010\}$ ,  $\{100\}$ , or  $\{001\}$  or equant with large pinacoidal faces; elongated along [100] or [001], to 15 cm, with about 40 forms recorded. Typically granular, nodular, parallel or divergent fibrous, massive. Twinning: Simple or repeatedly on  $\{011\}$ , common; contact twins rare on  $\{120\}$ .

**Physical Properties:** Cleavage: On {010}, perfect; on {100} nearly perfect; on {001} good to imperfect, yielding pseudocubic fragments. Fracture: Uneven to splintery. Tenacity: Brittle. Hardness = 3-3.5 D(meas.) = 2.98(1) D(calc.) = 2.95

**Optical Properties:** Transparent to translucent. *Color:* Colorless to pale blue or violet if transparent; white, mauve, rose, pale brown or gray from included impurities; colorless in transmitted light. *Streak:* White to pale gray. *Luster:* Pearly on {010}, vitreous to greasy on {001}; vitreous on {100}.

Optical Class: Biaxial (+). Pleochroism: For violet varieties; X = colorless to pale yellow or rose; Y = pale violet or rose; Z = violet. Orientation: X = b; Y = a; Z = c. Dispersion: r < v, strong. Absorption: Z > Y > X.  $\alpha = 1.567-1.574$   $\beta = 1.574-1.579$   $\gamma = 1.609-1.618$   $2V(\text{meas.}) = 42^{\circ}-44^{\circ}$ 

**Cell Data:** Space Group: Amma. a = 6.993(2) b = 6.995(2) c = 6.245(1) Z = 4

X-ray Powder Pattern: Synthetic.

3.499 (100), 2.849 (29), 2.3282 (20), 2.2090 (20), 1.8692 (16), 1.6483 (15), 1.7500 (11)

Chemistry:		(1)	(2)		(1)	(2)
	$SO_3$	58.37	58.81	CaO	41.13	41.19
	$\rm CO_2$	0.17		$\mathrm{FeS}_2$	0.02	
	$(Al, Fe)_2O_3$	0.06		Total	99.75	100.00

(1) Yonaibata mine, Hukusima Prefecture, Japan; after deduction of  $CO_2$  as calcite, corresponds to  $Ca_{0.99}S_{1.00}O_4$ . (2)  $CaSO_4$ .

**Occurrence:** A major component in sedimentary evaporite deposits and in the cap rocks above salt domes, commonly formed by dehydration of gypsum; in igneous rocks, fumarolic deposits, and in seafloor hydrothermal chimneys, also an alteration product in hydrothermal mineral deposits.

Association: Gypsum, halite, sylvite, polyhalite, dolomite, calcite, magnesite, celestine, sulfur.

**Distribution:** Numerous occurrences worldwide. In Austria, from Hall, Tirol, at Ischl and Hallein, Salzburg, and Aussee, Styria. In Germany, in Saxony-Anhalt, from Stassfurt-Leopoldshall and Douglashall, near Westeregeln; at Wathlingen, near Celle, Lower Saxony, and elsewhere. Gemmy crystals from the Simplon Tunnel, Valais, Switzerland. In Italy, from the Campiano mine, Boccheggiano district, Tuscany; on Vesuvius, Campania. From the Faraday mine, Bancroft, Ontario, Canada. In the USA, from Paterson, Passaic Co., New Jersey; in the Fairfax quarry, Centreville, Fairfax Co., Virginia; large deposits in the Carlsbad potash district, Eddy Co., New Mexico; at the Boiling Salt Dome, Wharton Co., Texas. From Naica, Chihuahua, Mexico. In the Salt Range, Punjab, India. On Mt. Pinatubo, Philippines. At Morococha, Peru.

Name: From the Greek for without water, in contast to hydrous calcium sulfate minerals.

Type Material: Mining Academy, Freiberg, Germany, 16538.

**References:** (1) Palache, C., H. Berman, and C. Frondel (1951) Dana's system of mineralogy, (7th edition), v. II, 424–428. (2) Chang, L.L.Y., R.A. Howie, and J. Zussman (1996) Rock-forming minerals, (2nd edition), v. 5B, non-silicates, 74–94. (3) Hawthorne, F.C. and R.B. Ferguson (1975) Anhydrous sulphates. II. Refinement of the crystal structure of anhydrite. Can. Mineral., 13, 289–292. (4) Kirfel, A. and G. Will (1980) Charge density in anhydrite, CaSO<sub>4</sub>, from X-ray and neutron diffraction measurements. Acta Cryst., 36, 2881–2890. (5) McMurdie, H.F., M.-C. Morris, E.H. Evans, B. Paretzkin, W. Wong-Ng, and C.R.Hubbard (1986) Standard X-ray diffraction powder patterns from the JCPDS research associateship. Powder Diffraction, 1, 267. All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise without the prior written permission of Mineral Data Publishing.